

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-264194

(43)Date of publication of application : 20.09.1994

(51)Int.Cl.

C22C 38/00

C22C 38/44

C22C 38/54

F16B 25/10

(21)Application number : 06-001611

(71)Applicant : NIPPON STEEL CORP

(22)Date of filing : 12.01.1994

(72)Inventor : TAKANO KOJI
SAKAKIBARA MIZUO
ARAKI SATOSHI
MATSUI TAKASHI
YOSHIMURA KOICHI
MURATA WATARU

(30)Priority

Priority number : 05 3442 Priority date : 12.01.1993 Priority country : JP

(54) HIGH STRENGTH MARTENSITIC STAINLESS STEEL EXCELLENT IN RUST RESISTANCE AND DRILLING TAPPING SCREW

(57)Abstract:

PURPOSE: To develop high strength martensitic stainless steel wire rod excellent in rust resistance by subjecting hot rolled wire rod stainless steel having a specified compsn. to annealing treatment for two times under specified temp. conditions.

CONSTITUTION: The hot rolled wire rod of stainless steel having a compsn. contg., by weight, 0.13 to 0.20% C, 0.1 to 0.5% Si, 0.1 to 2.0% Mn, 1.0 to 2.5% Ni, 12.0 to 16.0% Cr, 1.3 to 3.5% Mo and 0.06 to 0.13% N, and the balance Fe and in which ARI value expressed by the formulae 1, 2 and 3 is regulated to 16 to 21%, D1 value to <0%, M1 value to <0% and W1 value to <26.0% or contg. 0.001 to 0.010% B or 0.05 to 1.0% Ti and 0.05 to 1.0% Nb and in which W2 value expressed by the formula 5 is regulated to <26.0% is subjected to annealing for two times of holding under heating at 700 to 800° C and 600 to 750° C for 0.5 to 50hr. Cr carbides having 0.2μm grain size are precipitated, by which the martensitic stainless steel having 950N/mm² tensile strength and excellent in rust resistance can be produced.ARI = C + 1.4X_uD1 = C + 1.2Mn + 0.4Si + 1.2Al
- (0.5C + 1.2Mn + Ni + 0.12Mo) - 10.0M1 = Ni - 0.12C + 0.12Mn + 1.2N + 0.05(Cr - 1.5Si - 1.4Mo)
- 25.0

W1 = 2Mo + 12.8Cr + 6Mn + 6.3Si + Ni

W2 = 2Mo + 12.8Cr + 6Mn + 6.3Si + Ni + 12Ti + 12Nb

LEGAL STATUS

[Date of request for examination]

20.09.2000

BEST AVAILABLE COPY

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3340225

[Date of registration]

16.08.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]


Copyright (C); 1998,2003 Japan Patent Office

BEST AVAILABLE COPY


【図1】




【図2】



【図3】



【図4】



フロントページの続き

(72)発明者 松井 孝至
光市大字島田3434番地 新日本製鐵株式会
社光製鐵所内

(72)発明者 吉村 公一
光市大字島田3434番地 新日本製鐵株式会
社光製鐵所内

(72)発明者 村田 亘
光市大字島田3434番地 新日本製鐵株式会
社光製鐵所内